

DOW CORNING®

3140 RTV COATING

101-713/4

FEATURES

- * EXCELLENT DIELECTRIC PROPERTIES OVER A WIDE TEMPERATURE RANGE
- * GOOD ADHESION TO GLASS, CERAMICS, METAL AND MOST PLASTICS FOR INCREASED RELIABILITY
- * HIGH FLEXIBILITY TO REDUCE STRESS ON COATED COMPONENTS DURING THERMAL CYCLING
- * MIL-I-46058C
- * Self-levelling to provide an even coating with excellent point coverage
- * Non-corrosive
- * Resistant to moisture, corona, ozone and weathering
- * Clear
- * Solventless
- * Room temperature cure

DESCRIPTION

Dow Corning® 3140 RTV coating is a clear, flowable, one component silicone elastomer. This material reacts with moisture in the air to cure, giving a high strength, rubbery solid. It is easy to handle, requires no mixing or heating and does not contain any solvents.

Dow Corning 3140 RTV coating is flowable and self-levelling which allows it to be simply applied as a conformal coating to printed circuit boards or to encapsulate electronic assemblies. The non-corrosive cure mechanism produces non exothermic heat and as a result, it can be used in corrosion sensitive electronic equipment with no adverse effects.

APPLICATIONS

Dow Corning 3140 RTV coating is used for protecting corrosion sensitive components and printed circuit boards and for encapsulating small circuits or connectors. Typical applications include conformal coating for printed circuit boards and thick film hybrids, cushioning oscillator crystals and other fragile components. In addition, this material is used for sealing cable terminations in electronic enclosures and for repairing RTV silicone rubber encapsulation.

TYPICAL PROPERTIES

As Supplied

CTM 0364*	Consistency	Flowable
	Viscosity, mPa s	35000
	Coating Thickness per dip, mm	0.4
	Skin-Over Time, minutes	25
CTM 0095	Tack-Free Time, hours	1.5
	Cure Time, 0.5 mm thickness, hours	24
	Cure Time, 3.2 mm thickness, hours	72
	Full Cure, 3.2 mm thickness, days	7
CTM 0208	Non-Volatile Content, percent	98

Physical-after 7 days at 25°C and 50% relative humidity

	Colour	Clear
CTM 0022*	Specific Gravity, g/cm ³	1.05
CTM 0099	Durometer Hardness, Shore A	25
CTM 0137A	Tensile Strength, MPa	2.0
CTM 0137A	Elongation, percent	350
CTM 0159A	Tear Strength, die B, kN/m	3.6
CTM 0293	Peel Strength from primed aluminium, kN/m	4.22
CTM 0539	Thermal Conductivity (25°C to 100°C) W/m.K	0.12
	Volume Expansion (25°C to 100°C) 1/K	8.8 x 10 ⁻⁴

Electrical-after 7 days at 25°C and 50% relative humidity

CTM 0114	Electric Strength, kV/mm	20
CTM 0249	Volume Resistivity, ohm.cm	5.0 x 10 ¹⁴
CTM 0112	Permittivity at 25°C 100 Hz	2.64
	100 KHz	2.63
CTM 0112	Dissipation Factor at 25°C 100 Hz	0.0016
	100 KHz	0.0004

* In most cases, CTM's (Corporate Test Method) correspond to ASTM standard tests.
Copies of CTM procedures are available upon request.

These values are not intended for use in preparing specifications.

Specification Writers: Please contact Dow Corning Europe, La Hulpe, Belgium, before writing specifications on this product.

HOW TO USE

Substrate Preparation

Dow Corning 3140 RTV coating should always be applied to clean, dry surfaces. A satisfactory bond will usually be formed without using a primer on degreased surfaces. For maximum adhesion, however, the use of Dow Corning® 1204 primer is recommended as described below.

1. Thoroughly clean and degrease metal and plastic surfaces, then rinse all surfaces except plastic, with acetone (see Handling Precautions). Rubber surfaces should be roughened with sandpaper, then wiped with acetone and allowed to dry.
2. For maximum adhesion, apply Dow Corning 1204 primer (see Handling Precautions) to all surfaces except silicone rubber. Allow the primer to dry for 30-90 minutes at room temperature.

How to Apply

Dow Corning 3140 RTV coating is a flowable liquid and should be applied as a conformal coating to printed circuit boards or thick film hybrids by dipping. Slowly immerse the assembly into a bath of the silicone elastomer to avoid entrapment of air bubbles. After one minute, withdraw the assembly and allow the excess to drain back into the dip tank. Whilst draining, position assemblies having sharp points, such as soldered component leads, with the points facing downwards to obtain the best point coverage. Curing on the surface of the Dow Corning 3140 RTV coating in the dip tank can be minimised by maintaining a blanket of dry nitrogen above the silicone elastomer in the bath.

For individual component fixation or sealing applications, Dow Corning 3140 RTV coating can be applied directly from a collapsible tube fitted with a plastic nozzle which has been cut to the desired orifice size and shape.

1. Apply Dow Corning 3140 RTV coating in a uniform thickness. Best adhesion is obtained with an approximately 0.5 mm glue line. When bonding two surfaces, join the surfaces with enough uniform pressure to displace any excess adhesive.
2. Let the unit stand undisturbed at room temperature with at least 30 percent relative humidity to cure.

Cure

On exposure to moisture in the air, the surface of Dow Corning 3140 RTV coating will form a skin in about 25 minutes at room temperature with 50% relative humidity. At this point, the coating is no longer flowable and after 90 minutes under these conditions, the coating will become tack-free, allowing limited handling until the cure is fully complete.

Curing proceeds inward from the surface at a rate which depends upon the relative humidity, the degree of confinement and the thickness of the coating. Too little moisture or too thick an application will extend the cure time. Likewise, cure time is generally proportional to the degree of confinement if Dow Corning 3140 RTV coating is placed between two impermeable surfaces. The larger the unexposed area, the longer the cure time and an overlap of 25 mm represents the largest practical joint.

A 3 mm thickness of Dow Corning 3140 RTV coating will cure in 72 hours at room temperature and a relative humidity of at least 30 percent. Lower levels of relative humidity are not recommended. Optimum physical and electrical properties are reached after curing for 7 days at room temperature.

Repairability

Dow Corning 3140 RTV coating can be cut away with a sharp knife for repair or modification. Soaking the coated unit in Chloroethene⁽¹⁾, Freon⁽²⁾, toluene or similar halogenated or aromatic solvents (see Handling Precautions) will cause swelling and deterioration of the coating that will aid in its removal. The clean, dry surface may then be recoated with Dow Corning 3140 RTV coating.

⁽¹⁾ Registered trademark of Dow Chemical Co.
⁽²⁾ Registered trademark of E I DuPont de Nemours.

HANDLING PRECAUTIONS

Dow Corning 1204 primer is flammable. Keep away from heat and open flames. Use only with adequate ventilation. Avoid prolonged breathing of vapour and prolonged or repeated skin contact.

In addition, when using solvents, avoid heat, sparks and open flames. Always provide adequate ventilation. Obtain and follow hand-

ling recommendations from solvent supplier.

A Safe Handling Instruction sheets on Dow Corning 3140 RTV coating and Dow Corning 1204 primer should be obtained from your nearest Dow Corning sales office prior to use.

STORAGE AND SHELF LIFE

When stored in original unopened containers at or below 30°C, Dow Corning 3140 RTV coating has a shelf life of 6 months from date of shipment.

Refrigerated storage is not essential but will extend the useful life of this material. Containers should always be kept sealed when not in use. After a container of sealant has been opened, a plug of cured material may form in the nozzle or tube tip during storage. This is easily removed and does not affect the remaining contents.

PACKAGING

Dow Corning 3140 RTV coating is supplied in 3fl.oz., 10.7fl.oz., 310ml and 4.5 U.S. gal. containers.

IMPORTANT USERS PLEASE NOTE

The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since Dow Corning cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose.

You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it.

Dow Corning warrants only that its product will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranties. The user's exclusive remedy and Dow Corning's sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. Dow Corning will not be liable to consequential damages of any kind.

Suggestions of use should not be taken as inducements to infringe any patent.

DOW CORNING

DOW CORNING EUROPE
RUE GENERAL DE GAULLE 62
B-1310 LA HULPE, BELGIUM
TEL: (02) 655 21 11 TX: 22530
FAX: (02) 655 20 01

United Kingdom Dow Corning Limited, Kings Court, 185 Kings Road, Reading, Berks RG1 4EX.
Tel: (0734)6507251 Tx: 848340 DOWRDG G. Fax: (0734)575051
Dow Corning Limited, Caledonian House, Knutsford, Cheshire WA16 6AG Tel: (565)504 15 Tx: 665192, Fax: (565)633 405
Austria Dow Corning GmbH, Ghegastraße 3, A-1030 Wien, Tel: (0222)78 25 01 Tx: 133084 Fax: (0222)78 21 79.
France Dow Corning France S.A., Immeuble Britannia, 20 boulevard Eugene Deruelle, F-69432 Lyon Cedex 3.
Tel: 78 60 51 48 Tx: 300537/F Fax: 78 62 78 98
Dow Corning France S.A., 191 rue du 1^{er} Mai, F-92000 Nanterre Tel: (1)47 80 71 65 Tx: 610 758 Fax: (1)47 60 94 03.
Italy Dow Corning SpA, Palazzo Canova - Centro Direzionale, I-20090 Milano 2
Tel: (02)26 41 40 41 Tx: 330279 DOWSIL I Fax: (02)26 41 16 61
Spain Dow Corning Iberica S.A., Avda Diagonal 613, 5^o, E-08028 Barcelona, Tel.: (03)405 12 15 Tx: 50425 Fax: (03)405 38 94
West Germany Dow Corning GmbH, Rheingaustraße 53/Postfach 130332, D-6200 Wiesbaden 13
Tel: (0611)2371 Tx: 4186177 Fax: (0611)29682
Scandinavia & Benelux Dow Corning Europe, rue General de Gaulle 62, B-1310 La Hulpe, Belgium
Tel: (02)655 21 11 Tx: 22530 Fax: (02)655 20 08

05/91