Thick Film Chip Resistors — Anti-Sulfuration


Features

- High stability Thick Film Chip Resistor
- Special (patented) termination prevents sulfuration in a sulfur containing environment

Unit: inches (mm)

TCR ±100ppm

Specifications



	,									
	CRS0201	CRS0402	CRS0603	CRS0805	CRS1206	CRS1210				
L	0.024 ± .002	0.040 ± .002	0.063 ± .008	0.079 ± .008	0.126 ± .008	0.126 ± .008				
	(0.6 ± 0.05)	(1.0 ± 0.05)	(1.6 ± 0.2)	(2.0 ± 0.2)	(3.2 ± 0.2)	(3.2 ± 0.2)				
W	0.012 ± .001	0.020 ± .002	0.031 ± .008	0.050 ± .008	0.063 ± .008	0.098 ± .006				
	(0.3 ± 0.02)	(0.5 ± 0.05)	(0.8 ± 0.2)	(1.25 ± 0.02)	(1.6 ± 0.2)	(2.50 ± 0.15)				
Т	0.010 ± .002	0.014 ± .002	0.014 ± .004	0.018 ± .006	0.022 ± .006	0.022 ± .006				
	(0.25 ± 0.05)	(0.35 ± 0.05)	(0.45 ± 0.10)	(0.45 ± 0.15)	(0.57 ± 0.15)	(0.56 ± 0.15)				
С	0.006 ± .002	0.008 ± .004	0.010 ± .006	0.016 ± .008	0.018 ± .008	0.018 ± .008				
	(0.15 ± 0.05)	(0.2 ± 0.01)	(0.25 ± 0.15)	(0.4 ± 0.2)	(0.45 ± 0.2)	(0.45 ± 0.2)				
d	0.006 ± .002	0.008 ± .004	0.010 ± .006	0.012 ± .008	0.012 ± .008	0.012 ± .008				
	(0.15 ± 0.05)	(0.2 ± 0.01)	(0.25 ± 0.15)	(0.3 ± 0.2)	(0.3 ± 0.2)	(0.3 ± 0.2)				

Rating


Series	Rated Power at 70°C	Maximum Working Voltage	Maximum Overload Voltage	Operating Temperature Range	Resistance Range
CRS0201-20W	0.05W	25V	50V	-55°C ~ 150°C	$10\Omega \sim 1M\Omega$
CRS0402-16W	0.063W	50V	100V	-55°C ~ 150°C	1Ω ~ 1MΩ
CRS0603-16W	0.063W	75V	150V	-55°C ~ 150°C	1Ω ~ 1MΩ
CRS0805-10W	0.10W	150V	200V	-55°C ~ 150°C	1Ω ~ 1MΩ
CRS1206-8W	0.125W	175V	300V	-55°C ~ 150°C	1Ω ~ 1MΩ
CRS1210-4W	0.25W	200V	400V	-55°C ~ 150°C	1Ω ~ 1ΜΩ


NOTE: Markings on Thick Film Chip Resistors may have an internal lot identification code or the E-24 (5%) or E-96 (1%) marking code. If value identification is required, please consult your sales person for availability.

Values available in the E-24 Series that are crossover values (same value for 1% and 5%) will typically be marked with a 3-digit E-24 Series marking code.

Structure

No.		Description
1	Ceramic Substrate	96% Alumina
2 & 3	Inner Electrode	Silver Palladium (Ag-Pd)
4	Resistive Element	Ruthenium Oxide (RuO ₂)
5 & 6	Protective Coating	Boro-Silicate Glass
7	Side termination	Silver (Ag)
8	Resin Coating	Special (patented) anti-sulfuration coating Silver (Ag)
9	Middle Layer	Nickel (Ni)
10	Outer Layer	Tin (Sn) (100% Sn for Lead free)







e-mail: sales@venkel.com • www.venkel.com

Anti-Sulfuration Test Data

Venkel Ltd. manufacturers all Anti-Sulfuration Thick Film Chip Resistors to meet or exceed ASTM B809 testing criteria and guidelines.

Test Conditions:

Chip resistors are mounted on the test board with the power "ON" and kept in the atmosphere of 50° C, Relative Humidity of 95% and present in the atmosphere is $H_2S - 3PPM$.

10 pieces each of regular chip resistors and anti-sulfuration chip resistors were tested.

Hours >>	1,000	2,000	3,000	4,000	4,500	5,000	5,500	6,000	6,500	7,000	8,000	8,500	9,000
Regular chip resistors	0	0	0	0	X1	X2	X1	X1	Х3	X1	X1	ı	ı
Anti-sulfuration chip resistors	0	0	0	0	0	0	0	0	0	0	0	0	0

 \mathbf{O} = No failure. X1 = 1 failure. X2 = 2 failures. X3 = 3 failures.

Test Results:

Regular chip resistors start failing (open) from 4,500 hours and by 8,500 hours, all have failed (opened). anti-sulfuration chip resistors have no failures up to 9,000 hours and beyond.

